
PRODUCT SUBMITTAL SHEET

Product Type: Structural Track

Product Definition: 400T162-68 (33ksi)

CSI Code: 05 41 00



Profile Properties:

Web Depth (inside)	4.000 in	Yield Strength Fy:	33 ksi
Flange Width	1.625 in	Unit Weight	1.73 lb/ft
Web Depth (outside)	4.1426 in	Punchout Width / Length	None
Design Thickness	0.0713 in	Coating	G60 or G90
Thickness	68 mils (14 Ga)	Min. Steel Thickness	0.0677 in
Inside Bend Radius	0.1069 in	Tensile Strength Fu	45 ksi

Gross Section Properties:

Cross Sectional Area	Agross	0.5082 in2
Member weight per foot of length		1.73 lb/ft
Moment of Inertia. x-axis	Ix	1.3034 in4
Section Modulus. x-axis	Sx	0.6292 in3
Radius of Gyration. x-axis	rx	1.6015 in
Moment of Inertia. y-axis	Iy	0.1269 in4
Radius of Gyration. y-axis	ry	0.4996 in

Torsional Properties:

St. Venant Torsion Constant	J x 1000	0.8612 in4
Warping Constant	Cw	0.3752 in6
Distance Between Shear Axis and Neutral Axis	x0	-0.9117 in
Shear Center to Web Centerline	m	0.5569 in
Polar Radius of Gyration	r0	1.9093 in
Torsional Flexural Constant	β	0.7720
Limit of Unbraced Length	Lu	29.14 in

Effective Section Properties:

Effective Area	Aeff	0.4041 in2
Effective Moment of Inertia for Deflection	Ixe	1.1824 in4
Effective Section Modulus	Sxe	0.5404 in3
Allowable Bending Moment	Ma	10.6793 in.k
Allowable Shear Force	Vag	3341 lbs

Codes & Standards:

- Calculations are based on AISI S240-20 and AISI S100-16 (2020) w/S2-20.
- AISI S240-20 North American Standard for Cold-Formed Steel Structural Framing: Section A3 Material (ASTM A1003/A1003M); Section A4 Corrosion Protection (ASTM A653/A653M); Section A5 Products – thickness, shapes, tolerances, identification; Section C Installation (ASTM C1007).
- IBC 2024 International Building Code. ASTM C955. ASTM A1003. ASTM A653 SS Grade 33. Coating G60 or G90 per AISI S240 Section A4.
- ICC-ES ESR-5905 UMS Joists, UMS Studs and UMS Tracks.
- LEED / Sustainability Credits: Environmental Product Declaration S-P Code: S-P-00869
- Note: Tracks are manufactured without web punch-outs. Web depth designation is the inside-to-inside dimension; outside web depth = designation + 2 × design thickness (tolerance 0 to +1/8'').

Structural Track. The technical content of this literature is effective 10/30/2026 and supersedes all previous information.